FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

Date: 12-08-2015

1. TESTING OF FINE AGGREGATES :

Sub: Testing of Fine Aggregates.
{Project*: Development and Concrete Road Works at Vinayakanagar Air Force in Ward No11}

Ref. : Letter No. Testing/BUB/2015-16, dated 08-08-2015

Sample supplied to lab by: Sri.N.Keerthi, Contractor,
Bangalore.

Report required for: Assistant Executive Engineer,
Vidyaranyapura Sub-Division,
BBMP, Bangalore

TABLE - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	97.00	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	86.00	60-95	75-100	85-100	
01.18	72.00	30-70	55-90	75-100	
600. mic	48.00	15-34	35-59	60-79	
300.mic	18.20	5-20	8-30	12-40	
150.mic	3.00	0-10	0-10	0-10	

TABLE 1.2 ;

Sl No	Test Conducted	Sample	Results	Requirements as Per IS. Specification IS :383-1970 (Reaffirmed 2002)
1	Silt Content	001	1.45%	Not more than 8%
2.	Specific Gravity	----	2.58	-------

*As Furnished by Client.
The Results relate only to the items tested.

JE-11

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

Dr. MANJESH .L
ME (Civil Engg.), Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

1. TESTING OF COARSE AGGREGATES (40 mm): **Date: 12-08-2015**

Sub: Testing of Coarse Aggregates.
{Project*: Development and Concrete Road Works at Vinayakanagar Air Force in Ward No11}
Ref. : Letter No. Testing/BUB/2015-16, dated 08-08-2015
Sample supplied to lab by: Sri.N.Keerthi, Contractor,
Bangalore.
Report required for: Assistant Executive Engineer,
Vidyaranyapura Sub-Division,
BBMP, Bangalore

Table - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2002) % Passing	
	40 mm Sample	*Single size*	*Graded*
40mm	97.30	85-100	95 – 100
20mm	66.00	0 -20	30- 70
10mm	26.00	0 -5	10- 35
4.75mm	Nil	------	0 - 5

TABLE 1 2 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2002)
1.	Flakiness Index	As above	13.00%	Not to exceed 25 %
2.	Crushing value	----,,----	25.30%	Not to exceed 45 % for concrete other than for wearing surfaces and 30% for concrete for wearing surfaces

*As Furnished by Client.
The Results relate only to the items tested.

DEPARTMENT OF CIVIL ENGINEERING BANGALORE

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/ **Date: 12-08-2015**

1. TEST REPORT ON REINFORCEMENT STEEL:

Sub: Testing of Reinforcement Steel of diameter 12mm.
{Project*: Development and Concrete Road Works at Vinayakanagar Air Force in Ward No11}

Ref. : Letter No. Testing/BUB/2015-16, dated 08-08-2015

Sample supplied to lab by: Sri.N.Keerthi, Contractor,
Bangalore.

Report required for: Assistant Executive Engineer,
Vidyaranyapura Sub-Division,
BBMP, Bangalore

TABLE – 1

SL No	Details	For 12mm	
		Test Results	Min Req. as per IS 1786-2008
01	Observed diameter of bar	**12.0mm**	12.0mm
02	Observed Wt/m Length **Kg/m**	**0.890**	0.834
03	Proof stress/Yield stress, fy , **N/mm^2**	**558.0**	500.0
04	Bend/ Re bend Test	**Ok**	---
05	Percentage of Elongation, %	**20.50**	12.00
06	Ultimate Tensile Strength **N/mm^2**	**630.0**	545.0

*As furnished by Client.
The Results relate only to the items tested.

14.8.2015
Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16

Date: 17-08-2015

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Development and Concrete Road Works at Vinayakanagar Air Force in Ward No11}
Ref. : Letter No. Testing/BUB/2015-16, dated 08-08-2015
Sample supplied to lab by: Sri.N.Keerthi, Contractor,
Bangalore.
Report required for: Assistant Executive Engineer,
Vidyaranyapura Sub-Division,
BBMP, Bangalore

PHYSICAL TESTS ON CEMENT

Brand* : Birla
Grade * : 53
Type * : OPC
Date : 09-08-2015 to 16-08-2015

SL No	Name of Test	Results	Requirements as per IS 12269-1987
		Cement Sample	
1	Initial setting time	**135 min**	Shall not be less than 30 min
2	Final setting time	**230 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.30 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**1.60 mm**	Shall not be more than 10 mm
5	Compressive strength a) 3 days (average of three results) b) 7 days (average of three results)	**28.60 N/ Sq mm** **41.60 N/Sq mm**	Shall not be less than 27 N/Sqmm Shall not be less than 37N/Sqmm

*As Furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2015-16/

DATE: 21-09-2015

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (28 days Compressive Strength)
{Project*: Development and Concrete Road Works at Vinayakanagar Air Force in Ward No11}

Ref. : Letter No. Testing/BUB/2015-16, dated 21-09-2015

Sample supplied to lab by: Sri.N.Keerthi, Contractor,
Bangalore.

Report required for: Assistant Executive Engineer,
Vidyaranyapura Sub-Division,
BBMP, Bangalore

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1 :

Sl No	Location/ Identification *	Date of Casting*	Date of Testing	Age in Days	C/S Area in Mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	23-08-15	21-09-15	29	22500	525	23.33	**23.62**
	002	"	"	"	"	530	23.55	
	003	"	"	"	"	540	24.00	

*As Furnished by Client.
The Results relate only to the items tested.

DEPARTMENT OF CIVIL ENGINEERING BANGALORE

21/09/2015

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BUB/CTE/2015-16/

DATE: 23-09-2015

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (28 days Compressive Strength)
{Project*: Development and Concrete Road Works at Vinayakanagar Air Force in Ward No11}

Ref. : Letter No. Testing/BUB/2015-16, dated 22-09-2015

Sample supplied to lab by: Sri.N.Keerthi, Contractor,
Bangalore.

Report required for: Assistant Executive Engineer,
Vidyaranyapura Sub-Division,
BBMP, Bangalore

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1 :

Sl No	Location/ Identification *	Date of Casting*	Date of Testing	Age in Days	C/S Area in Mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	25-08-15	22-09-15	29	22500	530	23.33	**22.66**
	002	"	"	"	"	515	22.88	
	003	"	"	"	"	490	21.77	

*As Furnished by Client.
The Results relate only to the items tested.

DEPARTMENT OF CIVIL ENGINEERING BANGALORE

25/09/2015
Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com